

The Pro's Choice Since 1936

**SAKRETE®**

# Stucco - One Coat Fibered

SAKRETE® Stucco Premix One Coat is a factory blended mixture of portland cement, sand and fiber reinforced polymers, packaged in 80 lb. moisture resistant bags. SAKRETE® Stucco Premix One Coat includes the sand needed for application. Bulk sand is not required.

## SAFETY:

READ and UNDERSTAND the Material Safety Data Sheet (MSDS) before using this product. WARNING: Wear protective clothing and equipment. See HMIS block. For emergency information, call CHEMTREC at 800-424-9300 or 703-527-3887 (outside USA). KEEP OUT OF REACH OF CHILDREN.

## PREPARATION:

SAKRETE® Stucco Premix One Coat will be hand-troweled in ONE coat, to a minimum 3/8" thickness, over approved sheathings. The coating is applied at ambient temperatures ranging from 40 degrees to 110 degrees Fahrenheit. The weather resistant barrier is applied as set forth in section II B 11. Refer to:

- ASTM/ICBO D 4258 Surface Cleaning of Concrete before painting
- ASTM/ICBO C 926 Application of Portland Cement Plaster
- ACI 524R Guide to Portland Cement Plastering
- ASTM/ICBO C 1063 Specification for Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster
- ASTM/ICBO 4261 Surface Cleaning of Concrete Unit Masonry for Coating

## MIXING:

One (1) sack and enough water (approximately 1-2 gallons), machine mix to a working consistency. Uniform color depends on strict control of mixing and application. For best results, mix water accurately and uniformly. Maintain uniform mixing times.

## CURING:

Moist curing must be provided for approximately 24 hours after coating application.

## NOTE:

Weather and temperatures, amount of water used as well as care used in the application are all factors over which we have no control. We assume no warranty for finished work, expressed or implied. Our liability is limited to the replacement of defective materials.

**SHELF LIFE:** One year from date of manufacture.

## STORAGE:

Store in a tightly closed container off the floor in a dry place.

## PACKAGING:

80 lb. (36.2 kg) bag UPC: 7-64661-20280-6

## ENVIRONMENTAL ADVISORY:

Uncured or crushed cured cement is an environmental hazard, which may adversely affect fish and wildlife. Dispose of construction debris containing cement, including empty bags, at a permitted municipal disposal firm. Do not use crushed concrete as a fill near an aquatic habitat.

**WARNING! CAUSES IRRITATION** - Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Exposure may result in irritation of the skin, eyes or nasal passages from alkali in Portland cement. When wet, contact with the skin or eyes may result in irritation or burns. **FIRST AID:** In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get prompt medical attention; for skin, wash thoroughly with plenty of soap and water. **WARNING! HARMFUL IF INHALED** - Avoid breathing dust. Keep container closed. Use with adequate ventilation. Excessive exposure by inhalation over an extended period of time may result in the development of pulmonary diseases including pneumoconiosis and silicosis. Crystalline Silica has been classified by IARC and NTP as a carcinogen.

## LIMITED PRODUCT WARRANTY

The manufacturer warrants that this product shall be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose other than the general purpose for which it is intended. This warranty runs for one (1) year from the date the product is purchased. ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ON THIS PRODUCT IS LIMITED TO THE DURATION OF THIS WARRANTY. Liability under this warranty is limited to replacement of defective product or, at the manufacturer's option, refund of the purchase price. CONSEQUENTIAL AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.

The SAKRETE Companies  
866-SAKRETE  
866-725-7383  
www.sakrete.com

REV 3-10