

The Pro's Choice Since 1936



SAKRETE®

Trowelable Crack Filler Blacktop Mastic Patch

Trowelable Crack Filler can be used directly from the container. Smooths unsightly rough alligatored pavement areas. Adheres tightly to sides of properly prepared cracks and joints to help keep out moisture, reducing pavement break-up caused by freeze-thaw action.

For filling and sealing cracks up to 1 inch wide in blacktop and concrete surfaces such as driveways and parking areas. Repairs dips, rough surfaces and holes in blacktop driveways, parking areas, etc.

SAFETY:

READ and UNDERSTAND the Material Safety Data Sheet (MSDS) before using this product. WARNING: Wear protective clothing and equipment. See HMIS block. For emergency information, call CHEMTREC at 800-424-9300 or 703-527-3887 (outside USA). KEEP OUT OF REACH OF CHILDREN.

READ ALL DIRECTIONS BEFORE STARTING WORK

For best results, apply in dry, warm weather. Do not apply when rain is forecasted or when the ambient air temperature is expected to fall below 50° F (10° F) within 48 hours.

PREPARATION:

Clean all dirt, dust and loose materials from cracks or rough surfaces with a stiff broom or stream of water. Dampen the crack. Sweep out any standing water on the surface or in the crack before applying crack filler.

APPLICATION:

Fill cracks in area to be smoothed. Apply Trowelable Crack Filler with cement trowel or putty knife by pressing material into crevices to improve bond. For rough textured pavement areas, trowel over surface up to 1/8" thick. Thicker applications will require longer curing and may be damaged if rain occurs before surface cures. (Do not apply in cracks over 1 inch wide or on surfaces over 1/8 inch thick). Clean tools with water immediately after use. Hardened product remaining on tools may be removed with mineral spirits.

CURING:

Allow Trowelable Crack Filler to cure 48 hours before seal-coating. Curing time will vary with thickness of application. Surface will usually cure in 48 hours but weather and thickness may slow drying. Curing to full depth of cracks may take 5 to 7 days. Keep traffic off the repair area if possible during the curing period. If this cannot be done, sprinkle sand over the repair area to prevent tracking.

STORAGE:

STORAGE: Store in a tightly closed container off the floor in a dry place.

COLOR: Black

PACKAGING:

1 gallon (3.8 L) UPC: 2-64661-31264-7

REV 3-10

The Pro's Choice Since 1936



SAKRETE[®]

Trowelable Crack Filler Blacktop Mastic Patch

Contents:

Refined Coal Tar	CAS# 65996-93-2
Kaolin	CAS# 1332-58-7
Silica	CAS# 14808-60-7
Synthetic Polymers	(proprietary)
VOC Limit	500 g/l
Asphalt	CAS# 8052-42-4

ENVIRONMENTAL ADVISORY:

Uncured or crushed cured cement is an environmental hazard, which may adversely affect fish and wildlife. Dispose of construction debris containing cement, including empty bags, at a permitted municipal disposal firm. Do not use crushed concrete as a fill near an aquatic habitat.

WARNING! CAUSES IRRITATION - Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Exposure may result in irritation of the skin.

FIRST AID:
In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get prompt medical attention; for skin, wash thoroughly with plenty of soap and water. If irritation persists, get medical attention.

LIMITED PRODUCT WARRANTY

The manufacturer warrants that this product shall be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose other than the general purpose for which it is intended. This warranty runs for one (1) year from the date the product is purchased. ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ON THIS PRODUCT IS LIMITED TO THE DURATION OF THIS WARRANTY. Liability under this warranty is limited to replacement of defective product or, at the manufacturer's option, refund of the purchase price. CONSEQUENTIAL AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.

The SAKRETE Companies
866-SAKRETE

REV 3-10